

PE Film Parameter		PP Woven Fabric Parameter		
Test Item		Unit	Test Method	Standard
Thickness		mic	/	125±10
Dart Drop		g	ASTM D1709	≥1300
Tensile Strength (Warp / Weft)		MPa	ASTM D882	≥32
Elongation at Break (Warp / Weft)		%	ASTM D882	≥650
Tear Strength (Warp / Weft)		N	ASTM D1004	≥11
Yield Strength (Warp / Weft)		MPa	ASTM D882	≥9.0
Heat Seal Strength	8+2	N	ASTM D882	≥90.0
Small Holes after Rub Test	Maximum	pc	ASTM F392	≤12
Gram Weight		g/m2	GB/T 13762	180±5
Density		pc of thread/ inch	GB/T 13762	14X14
14X14 Strength	Warp	N/50mm	ASTM D5035	≥1700
	Warp	N/50mm	ASTM D5035	≥1700
Elongation at Break		%	ASTM D5035	15~25
Stitched Line Strength		N/50mm	ASTM D5035	≥1000



OEC Group Liquid Logistics Solutions
16910 Texas Ave., Suite B-1, Webster, TX 77598 TEL: 832.763.8609